

Core Colors



Colonial Red^Δ
SR: .34 IE: .86 SRI: 35



Banner Red
SR: .42 IE: .84 SRI: 45



Brandywine
SR: .26 IE: .85 SRI: 24



Patina Green^Δ
SR: .29 IE: .87 SRI: 29



Classic Green
SR: .26 IE: .84 SRI: 24



Hartford Green*
SR: .10 IE: .82 SRI: 2



Regal Blue
SR: .28 IE: .86 SRI: 27



Slate Blue
SR: .26 IE: .85 SRI: 24



Stone Gray^Δ
SR: .36 IE: .84 SRI: 37



Slate Gray^Δ
SR: .37 IE: .86 SRI: 39



Charcoal^Δ
SR: .32 IE: .85 SRI: 32



Matte Black
SR: .27 IE: .86 SRI: 26



Dark Bronze
SR: .26 IE: .84 SRI: 24



Mansard Brown^Δ
SR: .29 IE: .86 SRI: 29




Medium Bronze^Δ
SR: .30 IE: .87 SRI: 31




Sierra Tan^Δ
SR: .35 IE: .86 SRI: 37




Surrey Beige^Δ
SR: .40 IE: .86 SRI: 43




Sandstone^Δ
SR: .54 IE: .86 SRI: 63



Almond^Δ
SR: .63 IE: .86 SRI: 75



Bone White[□]
SR: .72 IE: .84 SRI: 87



Regal White[□]
SR: .68 IE: .86 SRI: 82

[†] Featuring a pearlescent mica finish; subject to premium pricing.

Colors shown are as close to actual colors as allowed by the printing process. Actual metal samples are available.

Colors may appear different when viewed at different angles and under different lighting conditions.

Due to product improvements, changes and other factors, we reserve the right to change or delete information herein without prior notice.



*All Standard Stocked colors are ENERGY STAR® approved except Hartford Green.

□ LEED® compliant for low slope and steep slope.

Δ LEED® compliant for steep slope only.

Mica Colors[†]



Pewter^Δ
SR: .36 IE: .85 SRI: 38




Bright Silver^Δ
SR: .60 IE: .77 SRI: 68



Silversmith^Δ
SR: .53 IE: .78 SRI: 59



Champagne^Δ
SR: .37 IE: .83 SRI: 38



Bright Copper^Δ
SR: .49 IE: .85 SRI: 55

Custom Colors



Can't find your color? Fabral can tackle the most challenging custom color orders, expertly matching your samples for limitless possibilities.

To learn more, contact FabralCore™ at 800.884.4484 or Fabral.com.

SR = Solar Reflectivity

IE = Initial Emissivity

SRI = Solar Reflective Index

FABRAL COLOR	SR	IE	SRI	STEEL			ALUMINUM			
				24GA.†	22GA.‡	18GA.‡	.032"†	.040"†	.050"†	.063"†
Regal White	.68	.86	82	●■▲◆	●	●	●■			●
Bone White	.72	.84	87	●	●	●	●	●	●	
Almond	.63	.86	75	●			●	●		
Sandstone	.54	.86	63	●■▲◆	●		●	●	●	
Surrey Beige	.40	.86	43	●◆	●		●	●	●	
Sierra Tan	.35	.86	37	●			●	●		
Medium Bronze	.30	.87	31	●■◆	●	●	●	●	●	●
Mansard Brown	.29	.86	29	●			●	●	●	
Dark Bronze	.26	.84	24	●■▲◆	●	●	●■	●	●	●
Matte Black	.27	.86	26	●	●		●	●		
Stone Gray	.36	.84	37	●			●			
Slate Gray	.37	.86	39	●◆			●	●		
Charcoal	.32	.85	32	●	●		●	●		
Slate Blue	.26	.85	24	●			●			
Regal Blue	.28	.86	27	●			●			
Patina Green	.29	.87	29	●			●			
Classic Green	.26	.84	24	●■	●		●	●		
Hartford Green	.10	.82	2	●			●			
Brandywine	.26	.85	24	●			●			
Colonial Red	.34	.86	35	●			●			
Pewter	.36	.85	38	●			●			
Bright Silver	.60	.77	68	●			●■			
Silversmith	.53	.78	59	●			●			
Champagne	.37	.83	38	●			●			
Bright Copper	.49	.85	55	●■			●■			

PAINT PERFORMANCE PROPERTIES	HOT DIPPED GALVANIZED STEEL OR GALVALUME®	ALUMINUM
Accelerated Weathering ASTM D 4587 (Drew Cycle Weatherometer)	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max
ASTM G 23	Hours: 5,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max	Hours: 5,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max
Salt Spray ASTM B 117	Hours: 1,000 Total Scribe: Rating 7 1/16" (1.6mm) Field: Rating 10, no blisters	Hours: 3,000 Total Scribe: Rating 10, no creepage Field: Rating 10, no blisters
Humidity ASTM D 2247	Hours: 2,000 Total Rating: 10, no blisters	Hours: 3,000 Total Rating: 10, no blisters
Formability ASTM D 4145	0T-3T	0T-3T
ASTM D 522 (Elongation over 1/8" mandrel)	No cracking No loss of adhesion	No cracking No loss of adhesion
Pencil Hardness ASTM D 3363	HB-2H	HB-2H
Abrasion Resistance ASTM D 968	55-75 Liters of falling sand	55-75 Liters of falling sand
Specular Gloss ASTM D 523	20-35 at 60°	20-35 at 60°
Reverse Impact ASTM D 2794	2 x Metal thickness in inch-lbs. No loss of adhesion	1 1/2 x Metal thickness in inch-lbs. No loss of adhesion
Flame Test ASTM E 84	Class A rated coating	Class A rated coating

† Standard Coil Width is 48.25"

‡ Standard Coil Width is 44.375"

● Available in Standard Coil Width.

■ Available in 40.25" Coil Width.

▲ Available in 38" Coil Width.

◆ Available in 44.375" Coil Width.

NOTES ON AVAILABILITY:

- 24ga, .032", .040", .050" & .063" are standard 48.25" in width, 22ga & 18ga are 44.375" in width for painted items.
- Standard inventory is non-embossed. Please contact us for the availability of stucco embossing.
- Protective strippable film is available upon request.
- Mica colors and Banner Red are subject to premium pricing.
- Subject to change without notice.
- Unpainted, acrylic coated, Aluminum-Zinc Alloy steel (AZ-55) is maintained in: 26ga x 20", 26ga x 28", 26ga x 48.25", 24ga x 20", 24ga x 24", 24ga x 28", 24ga x 48.25", 22ga x 44.375", 22ga x 48.25", 20ga x 44.375" and 18ga x 44.375".
- All colors are supplied in Medium Gloss (20-35 at 60°). Low Gloss available subject to minimum coating run.

Fabral® standard architectural colors and finishes feature 70% polyvinylidene fluoride (PVDF) resin paint systems to ensure long term color retention and performance. Custom colors and finishes are also available. Minimum quantities and set up charges may apply.

Fabral.com
800.844.4484

FABRAL®